



HAL
open science

Shape memory and thermomechanical properties of starch-based foams

Laurent Chaunier, Anne-Laure A.-L. Reguerre, Denis Lourdin

► **To cite this version:**

Laurent Chaunier, Anne-Laure A.-L. Reguerre, Denis Lourdin. Shape memory and thermomechanical properties of starch-based foams. 9. European Conference on Foams, Emulsions and Applications, Jul 2012, Lisbonne, Portugal. 1 p., 2012. hal-02804918

HAL Id: hal-02804918

<https://hal.inrae.fr/hal-02804918>

Submitted on 5 Jun 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

SHAPE MEMORY AND THERMOMECHANICAL PROPERTIES OF STARCH-BASED FOAMS

Laurent Chaunier, Anne-Laure Réguerre and Denis Lourdin

INRA-UR1268, Unité Biopolymères Interactions et Assemblages. F-44300 Nantes
chaunier@nantes.inra.fr

Shape-memory polymers are an emerging class of smart materials [Liu, 2007]. Recent studies evidenced the possible storage of residual stresses in vitreous starch, leading to shape memory capabilities [Chaunier, 2009; Véchambre, 2010]. In the present work, the shape recovery of starch-based extruded foams was investigated when triggered by heating in oil, or water bath. Its efficiency was linked to their thermo-mechanical properties.

Maize flour was formulated with sugars and extruded as dense and expanded materials ($\varnothing_{\text{die}}=2\text{mm}$, $T_{\text{die}}=170^\circ\text{C}$, $\text{SME}=190\text{J/g}$). When cooled below their glass transition temperature (T_g) at the outlet of the die, a first “permanent” shape S1 was obtained : straight cylinders ($L=50\text{mm}$). The moisture content was equilibrated at 9% (wb) under a stable relative humidity ($\text{RH}=59\%$ at 20°C). The density was 0.6g/cm^3 for the expanded products and 1.5g/cm^3 for the dense materials. T_g was measured by Differential Scanning Calorimetry (DSC) at 52°C . A second shape, S2, was given above T_g by bending each straight specimen to $\theta_{\text{max}}=180^\circ$. This “temporary” shape was fixed when cooling below T_g and the bent samples were stored at a low humidity level. Then, each specimen spontaneously recovered its “permanent” straight shape when heated or submitted to moisture uptake.

The shape recovery was assessed in thermostated bath by images acquisition and analysis (Fig.1-a), to determine the recovered angle (θ) and to obtain the recovery ratio (Rr), as presented on Eq.1 : $\text{Rr}=(\theta_{\text{max}}-\theta)/\theta_{\text{max}}*100$ (1).




Figure 1: Assessment of the recovered angle (θ) by images acquisition and analysis on immersed specimen in thermostated bath (a). Evolution of the recovery ratio, Rr, in oil bath at $T_g+50^\circ\text{C}$ (■) and in water at 85°C (□) (b).

An important recovery was obtained with starch-based foams when triggered by heating in oil bath ($\text{Rr}=80\%$ after 2min at $T_g+50^\circ\text{C}$, Fig.1-b). Values were less important in the case of their recovery in water ($\text{Rr}=46\%$ after 4min). This was mainly due to their loss of stiffness, because of the water sorption. It led to a decrease of the modulus, measured by DMA from $E'=2\text{GPa}$ to 0.3MPa , for the dense material constitutive of their gaseous cells walls. In the light of these results, starch-based foams can be designed with an interesting shape recovery, especially when triggered by heating. This opens the field of new self-deploying smart biodegradable foams, even being edible.

References

- Liu *et al*, Journal of Materials Chemistry, 17, 1543-1558, 2007.
- Chaunier *et al*, Starch/Stärke, 61, 116-118, 2009.
- Véchambre *et al*, Macromolecules, 43(23), 9854-9858, 2010.

EUFOAM2012 Topic : C - Particles in Foams, Solid Foams

Preferred type of presentation (Oral or Poster) : Oral